

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

**EP 1 090 889 B1**

(12)

**EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention  
of the grant of the patent:  
16.07.2003 Bulletin 2003/29

(21) Application number: 99919293.3

(22) Date of filing: 19.05.1999

(51) Int Cl.7: **C04B 14/10, C04B 24/38**

(86) International application number:  
PCT/ES99/00145

(87) International publication number:  
WO 99/059933 (25.11.1999 Gazette 1999/47)

(54) **ADDITIVE FOR SPECIAL PLASTERS AND MORTARS, COMPOSITIONS CONTAINING THE ADDITIVE AND UTILIZATION OF THE ADDITIVE IN SPECIAL PLASTERS AND MORTARS**  
**ADDITIVE FÜR BESONDERE GIPS- UND MÖRTELSORTEN, ZUSAMMENSETZUNGEN DIESE ENTHALTEND UND VERWENDUNG DERSELBEN IN SPEZIELLEN GIPS- UND MÖRTELSORTEN**  
**ADJUVANT POUR PLATRES ET MORTIERS SPECIAUX, COMPOSITIONS CONTENANT L'ADJUVANT ET UTILISATION DE L'ADJUVANT DANS LES PLATRES ET LES MORTIERS SPECIAUX**

(84) Designated Contracting States:  
AT BE CH DE DK ES FI FR GB GR IE LI NL PT SE

(30) Priority: 20.05.1998 ES 9801042

(43) Date of publication of application:  
11.04.2001 Bulletin 2001/15

(73) Proprietor: TOLSA, S.A.  
28031 Madrid (ES)

(72) Inventors:  
• ALVAREZ BERENGUER, António  
E-28660 Boadilla del Monte (ES)  
• LIMPO OROZCO, Francisco Javier  
E-28690 Brunete (ES)

• DEL VALLE ALVAREZ, Bernardo Enrique  
E-28020 Madrid (ES)  
• HIDALGO MARTIN, Manuel  
E-28020 Madrid (ES)

(74) Representative: Ungria Lopez, Javier et al  
Avda. Ramon y Cajal, 78  
28043 Madrid (ES)

(56) References cited:  
EP-A- 0 773 198 US-A- 4 028 127  
US-A- 5 290 350

• DATABASE WPI Week 8724, Derwent  
Publications Ltd., London, GB; AN 1987-166464  
& JP 62 098 000 A (NITTO BOSEKI CO LTD)

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

**EP 1 090 889 B1**

**Description**

[0001] The present invention fits in the field of compounds and compositions useful as conglomerate building materials, and more specifically in the sector of water retaining additives for conglomerate building materials such as special mortar and gypsum.

**PRIOR ART OF THE INVENTION**

[0002] In the last few years, filled conglomerate building material compositions are being used more and more in replacement of conglomerate building materials, since they have noteworthy advantages as to their placement conditions, such as workability, initial degree of adherence and water retaining power during kneading, etc., as well as in their final properties, such as for example their qualities of adherence, resistance and finish.

[0003] These filled conglomerate building material compositions include additives, additional to the components of traditional conglomerate building materials, that provide the above mentioned advantageous properties.

[0004] Within the different types of filled conglomerate building materials, there are some whose final properties require the use of a thickening agent and water retaining agent. Among these materials are special mortar and gypsum that are used in very different applications such as the bonding among enclosures or supports with different ceramic materials, facade coverings, repairing and engobing.

[0005] Gypsum and special mortar, such as glue mortar, conventionally comprise a series of additives, such as for example water retaining agents. A water retaining agent is a product that due to its molecular structure and to its surface properties bonds to the water by means of "weak bonds" and retains the water in the matrix of the conglomerates during the setting and hardening process. The rheology in the paste that is formed is improved. The water retaining additives conventionally used for conglomerate building materials such as special mortar and gypsum, are based on cellulose-like derivatives, no alternative thereto being known up until the present.

[0006] European patent application EP-A-0773198 describes a thickening system that contains at least a cellulose-like ether, a starch ether, thickening components and a layer silicate such as sepiolite, bentonite and other clay, that correspond to such an additive on the market.

[0007] JP-A- 6209 8000 discloses fireproof fiber boards made of a composition containing cellulose derivatives, colloid sepiolite or attapulgite water repellants, organic binders, inorganic fillers and flame retardants.

[0008] Cellulose-like derivatives provide, based on their thickening effects, greater consistency to conglomerate building materials aside from increasing their water retaining and adherence capacities. Nonetheless, cellulose-like derivatives have the disadvantage of being relatively expensive and therefore conglomerate building materials such as traditional mortar and gypsum, without or with less than the necessary doses of such derivatives, are still being used, despite their poorer qualities with respect to filled compositions, for many uses when the use of a sufficiently filled conglomerate composition would really be more appropriate.

[0009] U.S. patent US-A-5637144 describes a substitutive composition of asbestos that comprises water, water retaining agents and finely divided clay, especially bentonite, while U.S. patent US-A-4028127 describes a mixture of cement comprised of gypsum with the product resulted from reacting a guar hydroxyalkyl ether with glyoxal that is useful to cover up cracks and holes in surfaces. None of the compositions described in the above mentioned U.S. patents can be applied as mortar or gypsum.

**OBJECT OF THE INVENTION**

[0010] An object of the present invention is to overcome the inconveniences of conventional gypsum and special mortar, that comprise cellulose-like derivatives, by means of the replacement of such derivatives by a new additive that allows achievement of placement and final qualities at least similar to said conventional filled compositions and in turn allow a reduction of the total cost of the final compositions.

[0011] Another object of the invention is to make available a new additive that improves at least one of the placement and final qualities with respect to conventional gypsum and special mortar.

[0012] Another object of the invention is to make available a new additive for gypsum, special mortar, such as glue mortar, single layer.

[0013] The present invention also has the object of filled compositions comprising special mortar and gypsum that contain the additive as well as the use of the new additive in special mortar and gypsum.

**DESCRIPTION OF THE INVENTION**

[0014] The above defined objects are achieved by means of a new additive for gypsum and special mortars, free of cellulose-like derivatives, whose additive comprises at least a solid mineral component selected from among clay, and

at least a modified natural gum, in which the mineral component is rheological grade sepiolite the additive comprising

20-75%, and more preferably 35-60%, of the solid mineral component;  
25-80%, and more preferably 40-65%, of a modified natural gum.

[0015] The solid mineral component is preferably rheological grade sepiolite such as the one described for example in European patent applications EP-A-0454222 and EP-A-0107299, whose content is included in the present description by reference.

[0016] Rheological grade sepiolite, marketed for example by TOLSA, S.A., Madrid, Spain, under the trade mark PANGEL, and obtained from natural sepiolite by means of special micronization processes that substantially prevent breakage of the sepiolite fibers, disperses easily in water and other polar liquids, and has an external surface with a high degree of irregularity, a high specific surface, greater than 300 m<sup>2</sup>/g and a high density of active centers for adsorption, that provide it a very high water retaining capacity upon being capable of forming, with relative ease, hydrogen bridges with said active centers. The microfibrillar nature of the rheological grade sepiolite particles makes sepiolite a material with high porosity and low apparent density. Due to the above mentioned properties, rheological grade sepiolite is capable of forming high viscosity pastes with excellent thixotropic and pseudoplastic behavior. In accordance with the invention, it has been verified that, when rheological grade sepiolite is added, along with a modified natural gum, to conglomerate building materials such as special mortar and gypsum, the adhesiveness, cohesion, surface efficiency, stability and texture of the mortar and gypsum are improved.

[0017] Additionally, rheological grade sepiolite has a very low cationic exchange capacity and the interaction with electrolytes is very weak, which in turn causes rheological grade sepiolite not to be practically affected by the presence of salts in the medium in which it is found, and therefore, it remains stable in a broad pH range. This final characteristic proves to be of the utmost importance since the mediums in which they work have a high salt content.

[0018] The modified natural gum may be selected from among combinations of monosaccharides, glucose, mannose, galactose and/or glucuronic acid, modified by successive reactions of basification and etherification with ethylene oxide and/or propylene oxide and/or butylene oxide. Preferably, the modified natural gum is a galactomanane, in other words, polysaccharides formed exclusively by galactose and mannose and modified by etherification with polypropylene oxide.

[0019] These natural gums have a main chain substantially identical to the chemical structure of cellulose, but they differ from cellulose in that they have lateral chains of other monomers. Their most outstanding functional property is that of the rheological agent in aqueous fluids and that of being an effective water retaining agent.

[0020] Optionally, the additive according to the present invention may be complemented with other thickening agents such as for example modified starches or polyacrylamides.

[0021] The additive according to the present invention, may be prepared by means of mixing its components without any specific order of addition being necessary, for example, for 5 minutes in a V mixer until a homogeneous product is obtained.

[0022] In order to add the additive to a conglomerate building material such as for example a special mortar or gypsum, the additive may be mixed together with the aggregate and cement fractions during manufacturing in the case of special mortar or, in the case of gypsum, during the manufacturing of the gypsum. Likewise, the additive according to the present invention may also be added in situ during the mixing with the kneading water.

[0023] Inclusion of the additive of the present invention in conglomerate building materials, such as special mortar and gypsum, implies the following characteristics:

- Great water retaining capacity that allows the conglomerate building materials to have good properties in a fresh state and in a hardened state.
- Absence of segregation and exudation, based on the viscosity regulating and thixotropic qualities of the additive that contribute to the homogeneity of the composition of conglomerate materials.
- Workability based on an increase of the thixotropic nature provided to the conglomerate material by the additive, which permits a labor cost reduction in order to achieve a satisfactory final finish.
- Increase of covering capacity per unit of mass of the conglomerate material upon improving its thixotropy and plasticity.
- Possibility to obtain excellent final finishes with very smooth surface textures, upon the additive providing a soft and plastic consistency.
- Great adherence in the fresh state as well as in the hardened state.

[0024] The possibility of doing without cellulose-like derivatives in order to achieve the above mentioned qualities in conglomerate materials makes it possible to obtain a reduction of the cost of conglomerate material with regard to conglomerate materials that comprise cellulose-like derivatives.

**EMBODIMENTS OF THE INVENTION**

[0025] The present invention is additionally illustrated on the basis of the following embodiments.

Example 1: A 50 kg sample of the additive was prepared according to the invention by mixing in a V mixer for 5 minutes the following components:

24 kg of rheological grade sepiolite of TOLSA, S.A. Madrid (Spain)  
26 kg of hydroxypropyl guar obtaining a homogenous product.

Example 2: Two samples of mortar, one with a commercial cellulose-like derivative (TYLOSE 10004 MH of HOECHST AG) as an additive, and the other one with the additive according to the present invention prepared in accordance with example 1, were prepared. For this purpose, Portland cement, thick aggregates with a particle size smaller than 1 mm, fine aggregates with a particle size smaller than 0.55 mm, and respectively one of the above mentioned additives were mixed for 5 minutes, and each one of the samples were kneaded until glue mortar of the characteristics specified in the following table were obtained::

Table 1

| Sample | Portland Cement IIB-45A (p.p.) | Coarse sand (p.p.) | Fine sand (p.p.) | Water (p.p.) | Cellulose-like derivative (p.p.) | Additive of invention (p.p.) |
|--------|--------------------------------|--------------------|------------------|--------------|----------------------------------|------------------------------|
| I      | 310                            | 560                | 130              | 250          | 3                                | 0                            |
| II     | 310                            | 560                | 130              | 250          | 0                                | 6.3                          |

[0026] The cost of adding the additive per ton of glue mortar, was approximately 3,220 ptas./t for sample I, that is to say, for the conventional additive, and 2,250 ptas./t for sample II, that is to say, for the additive according to the present invention.

[0027] The properties of the glue mortar according to samples I and II were evaluated according to European standards for adhesives for ceramic tiles. The water retention, consistency, vertical slipping, adherence 28 days later and workability were tested after 20 minutes and 28 days after the glue mortar were prepared. The results are shown in the following table:

Table 2

| Sample | Water retention (%) | Consistency (mm) | Vertical slipping (mm) | Adherence 28 days (kg/cm <sup>2</sup> ) | Workability after 20 min. & 28 days (kg/cm <sup>2</sup> ) |
|--------|---------------------|------------------|------------------------|---|---|
| I      | 99.93               | 180              | 0                      | 11                                      | 9.1   |
| II     | 99.94               | 180              | 0                      | 11.1                                    | 9.0   |

[0028] The results show that the additive object of the present invention (sample II) provides at least the same properties as the conventional additive comprised of cellulose-like derivatives, but at a substantially lower cost.

Example 3: Two samples of glue mortar, one with a commercial cellulose-like derivative (METHOCEL HB of DOW CHEMICAL) as an additive, and the other one with the additive according to the present invention prepared in accordance with example 1 were prepared. For this purpose, Portland cement, coarse aggregates with a particle size smaller than 1 mm, fine aggregates with a particle size smaller than 0.5 mm, and respectively one of the above mentioned additives, were mixed for 5 minutes, and each one of the samples were kneaded until glue mortar with that characteristics that are specified in the following table were obtained:

Table 3

| Sample | Portland Cement IIB-45A (p.p.) | Coarse sand (p.p.) | Fine sand (p.p.) | Water (p.p.) | Cellulose-like derivative (p.p.) | Additive of invention (p.p.) |
|--------|--------------------------------|--------------------|------------------|--------------|----------------------------------|------------------------------|
| III    | 200                            | 600                | 200              | 250          | 2.5                              | 0                            |
| IV     | 200                            | 600                | 200              | 250          | 0                                | 5.25                         |

[0029] The cost of adding the additive per ton of glue mortar, was approximately 2,875 ptas./t for sample III, that is

to say, for the conventional additive, and 2,200 ptas/t for sample IV, that is to say, for the additive according to the present invention.

[0030] The properties of the glue mortar according to samples III and IV were evaluated according to European standards for adhesives for ceramic tiles. The water retention, consistency, vertical slipping, adherence 28 days later and workability were tested after 20 minutes and 28 days after the glue mortar were prepared. The results are shown in the following table:

Table 4

| Sample | Water retention (%) | Consistency (mm) | Vertical slipping (mm) | Adherence 28 days (kg/cm <sup>2</sup> ) | Workability after 20 min. & 28 days (kg/cm <sup>2</sup> ) |
|--------|---------------------|------------------|------------------------|---|---|
| III    | 99.93               | 180              | 0                      | 12.2                                    | 10.0  |
| IV     | 99.93               | 180              | 0                      | 12.0                                    | 10.3  |

[0031] The results show that the additive object of the present invention (sample IV) provides at least the same properties as the conventional additive comprised of cellulose-like derivatives, but at a substantially lower cost.

## Claims

1. An additive for gypsum and special mortars that comprises a solid mineral component selected from among clay, and at least a modified natural gum, wherein the mineral component is a rheological grade sepiolite and the additive is free of cellulose derivatives, the additive comprising

20-75% by weight of the solid mineral component;  
25-80% by weight of modified natural gum.

2. An additive according to claim 1, **characterized in that** it comprises

35-60% by weight of the solid mineral component;  
40-65% by weight of modified natural gum.

3. An additive according to claim 1, 2 or 3, **characterized in that** the modified natural gum is at least one combination of at least two monosaccharides, glucose, mannose, galactose, and glucuronic acid, modified by etherification.

4. An additive according to claim 3, **characterized in that** the combination of monosaccharides is etherified with an alkylene oxide selected from among ethylene oxide, propylene oxide and butylene oxide.

5. An additive according to claim 3, **characterized in that** the monosaccharide combination is a galactomanane.

6. An additive according to claim 1 or 2, **characterized in that** the modified natural gum is modified guar gum.

7. A filled composition of conglomerate building material selected from among gypsum and special mortar, that comprises a fraction selected from among a cement fraction, a gypsum fraction and an aggregate fraction, **characterized in that** it also comprises 0.05-1.2% by weight of the additive defined in any of claims 1 to 6.

8. A filled composition according to claim 7, **characterized in that** it comprises 0.2-0.9% by weight of the additive.

9. Use of an additive according to any of the claims 1-7, as a component in a special mortar.

10. Use of an additive according to any of claims 1-6 as a component in gypsum.

## Patentansprüche

1. Additiv für Gips und Spezialmörtel, welches eine feste mineralische Komponente, ausgewählt aus Ton, und mindestens einen modifizierten Naturgummi umfasst, wobei die mineralische Komponente ein Sepiolith rheologischer

Qualität (rheological grade sepiolite) ist und das Additiv frei von Cellulosederivaten ist, wobei das Additiv umfasst

20-75 Gew.-% der festen mineralischen Komponente;  
25-80 Gew.-% modifizierten Naturgummi.

2. Additiv nach Anspruch 1, **dadurch gekennzeichnet, dass** es umfasst

35-60 Gew.-% der festen mineralischen Komponente;  
40-65 Gew.-% modifizierten Naturgummi.

3. Additiv nach Anspruch 1, 2 oder 3, **dadurch gekennzeichnet, dass** der modifizierte Naturgummi mindestens eine Kombination von mindestens zwei Monosacchariden, Glucose, Mannose, Galactose und Glucuronsäure, modifiziert durch Veretherung, ist.

4. Additiv nach Anspruch 3, **dadurch gekennzeichnet, dass** die Kombination von Monosacchariden mit einem Alkylenoxid verethert ist, das ausgewählt ist aus Ethylenoxid, Propylenoxid und Butylenoxid.

5. Additiv nach Anspruch 3, **dadurch gekennzeichnet, dass** die Monosaccharidkombination ein Galactomannan ist.

6. Additiv nach Anspruch 1 oder 2, **dadurch gekennzeichnet, dass** der modifizierte Naturgummi modifizierter Guar-gummi ist.

7. Gefüllte Zusammensetzung eines Baumaterialkonglomerats (conglomerate building material), ausgewählt aus Gips und Spezialmörtel, welches eine Fraktion umfasst, die ausgewählt ist aus einer Zementfraktion, einer Gipsfraktion und einer Zuschlagfraktion, **dadurch gekennzeichnet, dass** sie auch 0,05-1,2 Gew.-% des in einem der Ansprüche 1 bis 6 definierten Additivs umfasst.

8. Gefüllte Zusammensetzung nach Anspruch 7, **dadurch gekennzeichnet, dass** sie 0,2-0,9 Gew.-% des Additivs umfasst.

9. Verwendung eines Additivs nach einem der Ansprüche 1-7 als Komponente in einem Spezialmörtel.

10. Verwendung eines Additivs nach einem der Ansprüche 1-6 als Komponente in Gips.

## Revendications

1. Adjuvant pour plâtre et mortiers spéciaux comprenant un composant minéral solide choisi parmi les argiles, et au moins une gomme naturelle modifiée, dans lequel le composant minéral est une sépiolite de qualité rhéologique et l'adjuvant est exempt de dérivés celluloses, l'adjuvant comprenant :

de 20 à 75% en poids du composant minéral solide ;  
de 25 à 80% en poids de gomme naturelle modifiée.

2. Adjuvant selon la revendication 1, **caractérisé en ce qu'il** comprend :

de 35 à 60% en poids du composant minéral solide ;  
de 40 à 65% en poids de gomme naturelle modifiée.

3. Adjuvant selon la revendication 1, 2 ou 3, **caractérisé en ce que** la gomme naturelle modifiée est au moins une combinaison d'au moins deux monosaccharides, de glucose, de mannose, de galactose, et d'acide glucuronique, modifiée par étherification.

4. Adjuvant selon la revendication 3, **caractérisé en ce que** la combinaison de monosaccharides est étherifiée avec un oxyde d'alkylène choisi parmi l'oxyde d'éthylène, l'oxyde de propylène et l'oxyde de butylène.

5. Adjuvant selon la revendication 3, **caractérisé en ce que** la combinaison de monosaccharides est un galactomannane.

6. Adjuvant selon la revendication 1 ou 2, **caractérisé en ce que** la gomme naturelle modifiée est une gomme de guar modifiée.
- 5 7. Composition fillérisée d'un matériau de construction aggloméré choisi parmi le plâtre et un mortier spécial, laquelle comprend une fraction choisie parmi une fraction de ciment, une fraction de plâtre et une fraction de granulat, **caractérisée en ce qu'elle** comprend également de 0,05 à 1,2% en poids de l'adjuvant défini dans l'une quelconque des revendications 1 à 8.
- 10 8. Composition fillérisée selon la revendication 7, **caractérisée en ce qu'elle** comprend de 0,2 à 0,9% en poids de l'adjuvant.
9. Utilisation d'un adjuvant selon l'une quelconque des revendications 1 à 7, comme composant dans un mortier spécial.
- 15 10. Utilisation d'un adjuvant selon l'une quelconque des revendications 1 à 6 comme composant dans du plâtre.

20

25

30

35

40

45

50

55